

## 大同特殊鋼、DC53(8%Crダイス鋼) 1035°C焼入 高温焼き戻し硬さデータ

		C	Si	Mn	Ni	Cr	W	Mo	V
DC53									

焼入は中日本炉工業、N VF-30P N2ガス加圧冷却式真空炉、焼入温度 1035°C 保持50分 冷却N2ガス130KPa

焼き戻し炉は、サーマル。TAF-5 大気強制循環式を使用。保持時間は炉の温度で各120分

サブゼロはフロンティアエンジニアリング、M-1型 LN2サブゼロ装置

### ■サブゼロ無し

戻し温度	焼入硬さ	1回目	2回目	3回目
400°C	63.3	59.8	59.8	59.8
480°C	63.2	60.5	61.1	61.0
485°C	63.5	60.8	61.2	61.4
490°C	63.4	60.8	61.2	61.3
495°C	63.1	61.0	61.4	61.5
500°C	63.2	61.3	61.8	61.9
505°C	63.5	61.3	61.9	62.0
510°C	63.2	61.2	61.8	62.0
515°C	63.2	61.5	61.8	62.1
520°C	63.3	61.7	62.1	62.1
525°C	63.2	62.2	62.2	62.2
530°C	63.1	61.6	62.0	61.7
535°C	63.6	62.1	61.6	61.2
540°C	63.1	61.9	61.3	61.0
545°C	63.3	61.6	60.6	59.6
550°C	63.8	61.2	60.1	59.0
560°C	63.7	60.9	59.2	57.5
570°C	63.7	59.8	56.7	54.6

### ■サブゼロ-75°C 保持120分

戻し温度	サブゼロ	1回目	2回目	3回目
400°C	64.8	61.9	62.0	62.1
480°C	65.3	62.6	62.7	62.7
485°C	65.2	62.7	62.8	62.9
490°C	65.2	62.6	62.9	62.9
495°C	64.6	62.4	62.7	62.8
500°C	65.1	62.6	62.6	62.5
505°C	64.7	62.5	62.3	62.1
510°C	64.5	62.4	61.9	61.7
515°C	64.9	62.7	62.0	62.0
520°C	64.7	62.2	61.7	61.5
525°C	64.7	61.8	61.1	60.6
530°C	64.6	61.4	60.6	59.9
535°C	65.0	61.4	60.3	59.7
540°C	65.0	61.1	60.1	59.2
545°C	65.3	60.8	59.8	58.7
550°C	65.0	59.9	58.6	58.2
560°C	65.1	58.9	57.0	55.8
570°C	65.1	57.4	55.1	53.3

### ■サブゼロ-130°C 保持120分

戻し温度	サブゼロ	1回目	2回目	3回目
400°C	64.9	61.9	61.9	62.0
480°C	64.8	62.5	62.5	62.4
485°C	64.9	62.3	62.6	62.4
490°C	64.8	62.6	62.8	62.8
495°C	64.3	62.5	62.4	62.4
500°C	64.9	62.7	62.6	62.6
505°C	64.7	62.8	62.8	62.5
510°C	64.5	62.6	62.5	62.4
515°C	64.7	62.6	62.2	61.9
520°C	64.5	62.1	62.0	61.6
525°C	64.6	61.8	61.5	60.9
530°C	64.8	61.4	60.6	60.1
535°C	64.7	61.3	60.3	59.7
540°C	64.9	61.1	59.9	59.1
545°C	65.0	61.0	59.4	58.5
550°C	64.6	59.9	58.3	57.5
560°C	65.0	59.4	57.3	55.9
570°C	64.7	56.9	54.3	52.6

注意;データは、山形精研(株)が上記条件で取った物です。参考のみにして下さい。